

No. : XMIN2212009523CM

Date : Dec 16, 2022





CUSTOMER NAME:KENBROCK PTY LTDADDRESS:17 CATO ST, HAWTHORN EAST VIC 3123

Sample Name : CUSHION STONE

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*\*\*\*

Date of Receipt	:	Dec 09, 2022
Testing Start Date	:	Dec 09, 2022
Testing End Date	:	Dec 16, 2022
Test result(s)	:	For further details, please refer to the following page(s) (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd Xiamen Branch Testing Center

an

Bryan Hong Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <u>http://www.sgs.com/en/Terms-and-Conditions.aspx</u> and, for electronic format documents, advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits to Cilent's instructions, if any. The Company's sole responsibility is to its Colent and this document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307 1443. or email: CN\_Docuberke%ass.com

No.31Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765380 www.sgsgroup.com.cn 中国•福建•厦门•火炬(期安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com



No. : XMIN2212009523CM


Date : Dec 16, 2022

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result	
1	Oil-wet ramp test	AS 4586-2013 Amdt 1- 2017 Annex D	See result	
2	Wet pendulum test	AS 4586-2013 Amdt 1-2017 Annex A	See result	

**Original Sample Photo:** 





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/an/Terms-and-Conditions/Terms-end-Conditions

No.31 Xiangtong Read, XiargAn Torch Industrial Zone, Xianen, Fujian Province, China. 36 1101 t (86-582) 5765837 f (86-592) 5765380 www.sgsgroup.com.cn 中国・福建・厦门・火炬(期安)产业区期虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765380 e sgs.china@sgs.com



No. : XMIN2212009523CM Date : Dec 16, 2022 Page: 3 of 4

1.Test Item: Oil-wet ramp test

Sample Description: See photo

Test Method: AS 4586-2013 Amdt 1- 2017 Annex D

**Test Condition:** 

Specimen: 500mm×500mm, 2pcs form a testing surface 1000mm×500mm, see photo

Testing surface: see photo

Testing direction: see photo

Test result:

Test item(s)	Test result(s)	Classification
Slip resistance (oil-wet ramp test)	Critical angle of inclination: 15.0°	R10

#### Classification of pedestrian surface materials according to the oil-wet inclining platform test:

Slip resistance assessment group	Angle(degrees)		
No classification	X<6°		
R9	6°≤X<10°		
R10	10°≤X<19°		
R11	19°≤X<27°		
R12	27°≤X<35°		
R13	X≥35°		



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-end-Conditions

No.31Xianghong Read, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765880 www.sgsgroup.com.cn 中国•福建•厦门•火炬(期安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765880 e sgs.china@sgs.com



No. : XMIN2212009523CM Date : Dec 16, 2022 Page: 4 of 4

2.Test Item: Wet pendulum test

Sample Description: See photo

Test Method: AS 4586-2013 Amdt 1-2017 Annex A

**Test Condition:** 

Specimen: 200mm×150mm, 6pcs

Type of slider: slider 96 (4S rubber)

Testing surface: see photo

Testing direction: see photo

#### Test result:

Specimens identification No.	1	2	3	4	5	6
Mean of British Pendulum Number (for each test surface)	30	31	30	29	31	29
Slip resistance value (SRV "wet")	30					
Class			Р	2		

### Classification of pedestrian surface materials according to the wet pendulum test:

Class	Pendulum SRV (slider 96)
P5	>54
P4	45-54
P3	35-44
P2	25-34
P1	12-24
P0	<12

\*\*\*\*\*\*\*\* End of report\*\*\*\*\*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sos.com/en/Terms-and-Conditions aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sos.com/en/Terms-and-Conditions/Terms-end-Conditions/T

No.31Xianghong Read, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5765857 f (86-592) 5765880 www.sgsgroup.com.cn 中国•福建•厦门•火炬(期安)产业区翔虹路31号 邮编:361101 t (86-592) 5765857 f (86-592) 5765880 e sgs.china@sgs.com